

Avery Dennison® MPI2600 Series Film

Revision: 17

Dated: 12/02/25

Uses:

Avery Dennison MPI2600 Series Film is a tough, scuff-resistant, flexible, white premium calendered vinyl film designed for wall graphic applications. MPI2610 and 2611 have a smooth luster finish, while the MPI 2630 & 2631 Textured films offer a unique Canvas, Crushed Stone or Stucco look at ordinary wall graphics. The MPI2630 Crushed Stone and Stucco are also approved for use as short term indoor floor graphics.



Face Film: 6.0 to 8 mil (152-203µm) calendered



Adhesive: Acrylic (clear)
MPI2610 - Permanent
MPI2611 - Removable
MPI2630 - Permanent
MPI2631 - Removable



Liner: 90# StaFlat™



Durability: See chart on page 4



Shelf Life: 2 years from date of manufacture

Application Surfaces: Flat

Features

- 100% opacity, completely covers whatever is underneath
- Luster Finish (MPI 2610 & 2611)
- Textured finish (MPI 2630 & MPI 2631)
- Great image clarity and color pop
- Dimensionally stable liner for easy converting
- [ICC profiles available on the Avery Dennison website](#)
- ASTM E84 Class 1 or A rating (MPI 2611, MPI 2630 Stucco & Canvas, MPI 2631 Stucco, Canvas and Crushed Stone)
- ASTM E84 Class 2 or B rating (MPI 2630 Crushed Stone)
- CAN ULC S102.2 (MPI 2611) - Flame Spread Rating: 10, Smoke Developed Classification: 40
- MPI 2611 meets the requirements of IMO FTP Code Part 2 & 5 for all material categories
- MPI2630 Crushed Stone and Stucco meet UL 410 Standard for slip resistance of floor surface materials

Conversion

- Latex inkjet
- Solvent based inkjet
- Mild/Eco Solvent inkjet
- UV inkjet

To achieve the best possible print quality, please make sure the correct ICC Profile and printer setting are used.

Common Applications

- Wall Murals
- POP/ Trade Show
- Indoor floor graphics

Product Data Sheet

Page 1 of 5




Avery Dennison® MPI2600 Series Film

Revision: 17

Dated: 12/02/25

Physical Characteristics

Data represents average values where applicable, and is not intended for specification purposes.

Property	Measurement	Typical Value
Caliper, face		MPI 2610 & 26111 – 6.0 mil (152-203 µm) Canvas & Stucco – 6.0 mil (152 µm) Crushed Stone - 8.0 mil (203 µm)
Caliper, adhesive		1.0mil (25 µm)
Dimensional stability		<0.065”(1.651 mm) Note: Ink loads in excess of 250% may cause increased shrinkage and/or increased initial adhesion of the printed film
Tensile at Yield		4.0 - 8.0 lb/in (0.7–1.5 kg/cm)
Elongation		
Gloss	Hunter Gloss @ 60 degrees	MPI2610 & 2611 = 15 GU MPI2630 & 2631 = 4 GU
Adhesion	Stainless Steel 15 min 24 hr	Removable - 0.5 - 1.0 lbs/in (175 N/m) Permanent - 1.0 lbs/in(175 N/m) Removable - 1.5 lbs/in (262 N/m) Permanent - 4.0 lbs/in (700 N/m)
Flammability	FMVSS 302 ASTM E-84 CAN ULC S102.2 IMO FTP Code Part 2 & 5	Self Extinguishing Class 1 or A rating: MPI2610, 2611, MPI 2630 Stucco & Canvas, MPI2631 Stucco, Canvas and Crushed Stone Class 2 or B rating: MPI 2630 Crushed Stone MPI2611 Flame Spread Rating: 10 , Smoke Developed Classification: 40 MPI2611 meets the requirements for all material categories
Shelf-Life		2 years from date of manufacture (when stored at the following temperatures and humidity conditions 68°-77° F (20° - 25° C) and 50±5%R. H.)
Durability	Vertical Exposure	See chart on page 4
Min. Application Temperature		40° F (4° C)
Service Temperature		-40° to 180°F (-40° to 82° C)(Reasonable range of temperatures which would be expected under normal environmental conditions).
Chemical resistance		Resistant to most mild acids, alkalis, and salt solutions
Slip Resistance	UL 410 MPI2630 Crushed Stone & Stucco	 <p>CLASSIFIED UL FLOOR COATING AND FINISHING MATERIAL AS TO SLIP RESISTANCE ONLY UL Reference # 16GH</p>
Compliance		California Proposition 65
MSDS		MSDS Article Letter

Product Data Sheet

Page 2 of 5



Avery Dennison® MPI2600 Series Film

Revision: 17

Dated: 12/02/25

Removability for wall applications

Avery Dennison does not guarantee removability from the following substrates:

- Surfaces with poor paint-to-substrate adhesion
- Wallboard
- Existing graphics that must remain intact; damage to existing graphic when film is removed
- Aged paint or metal that may have surface oxidation or chalking
- Outdoor, horizontal surfaces

Related Documents

The following Avery Dennison literature will provide complete information to the user for proper application, storage, and other requirements and is available upon request from your Avery Dennison representative or from the [Avery Dennison® website](#).

Document Title	Instructional Bulletin
Storage, Maintenance, and Cleaning of PVC Films	1.20
Premask Recommendations	5.50
Wall Graphics	6.50

Expected Durability & Lamination Requirements

Description	Unprinted Durability (Indoor)	Printed Expected Durability for Indoor Wall Applications	Printed Expected Durability for Indoor Floor Applications	Laminate
MPI2610 & 2611	4 years	Up to 3 years	NA	Yes (Use DOL 1000 series or DOL2000 series)
MPI 2630 Canvas, Crushed Stone, Stucco	4 years	Up to 2 years	Up to 3 months	No
MPI 2631 Canvas	4 years	Up to 2 years	NA	No

Additional Notes

Avery Dennison does not warrant damage to the interior wall surface caused by removing film even if a removable adhesive was used. Removing a graphic can cause damage to the wall. Due to the variety of wall surfaces Avery Dennison® cannot guarantee damage free removal. The amount of damage can be reduced or eliminated by following the inspection, cleaning and preparation guidelines provided in Instructional Bulletin #6.50.

Product Data Sheet

Page 3 of 5



Avery Dennison® MPI2600 Series Film

Revision: 17

Dated: 12/02/25

Discontinued

Description	Date
MPI2631 Removable Stucco	05/01/20

Description	Date
MPI2631 Removable Crushed Stone	05/01/20

Revisions are italicized

Avery Dennison is a registered trademark of Avery Dennison Corporation.